



Product Description:

IB Energy Board II is a closed-cell polyisocyanurate foam core integrally bonded to non-asphaltic, fiber-reinforced organic felt facers. IB Energy Board II is a product that offers Long-Term-Thermal-Resistance (LTTR) values from 5.7 to 26.8.

Features:

- Excellent LTTR to thickness ratio
- Sustainable Building Material
- Zero Ozone Depletion Potential (ODP) from blowing agent
- Virtually no Global Warming Potential (GWP)*
- Reduces cooling and heating loss transmission through roofing assemblies
- Covered component under the IB Total Systems Warranty
- Can be used for mechanically attached, induction attached, fully adhered, or ballasted roof assemblies

Packaging:

In 4' x 4' and 4' x 8' panels - Number of panels per pallet varies based on thickness.

IB Energy Board II is shrink-wrapped and job site delivered.

Approvals:

- ASTM C1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi)
- FM Standard 4450/4470 Approved
- GWP of IB Energy Board II is negligible and is considered zero (0) by the U.S. EPA.
- Miami-Dade County Approved
- State of Florida Product Approval (FL2534)
- UL Standard 263 (ASTM E119) Fire Resistance Classification
- UL Standard 790 (ASTM E108) Roofing Systems Classification
- UL Standard 1256 Classification Construction
- UL Standard 1897 Uplift Resistance



Refer to SDS for more information concerning Ozone Depletion Potential. IB EnergyBoard is trademark of IB Roof Systems. IB EnergyBoard II is also designated with suffixes of A, H, or J to designate its point of origin within the IB Roof System distribution network.

Product details stated are nominal as manufactured, and the results of tests and/or calculations and therefore are non-binding and do not represent a guarantee or warranted characteristics. User and/or designer are responsible for confirming suitable performance for specific application and conforming with all applicable laws and regulations.

Typical Physical Properties*			
Property	Test Method	Result (nom)	
Dimensional Stability	ASTM D2126 (7 days)	< 2%	
Compressive Strength	ASTM D1621	20 psi or 25 psi	
Water Absorption	ASTM C209 & D2842	< 1.5%	
Water Vapor Transmission	ASTM E96	< 1.5 perm	
Product Density	ASTM D1622	2.0 pcf	
Flame Spread	ASTM E84 (10 min.)	< 75	
Smoke Development	ASTM E84 (10 min.)	< 450	
Tensile Strength	ASTM D6123	730 psf	
Service Temperature		-100° to 250°F	

*Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of ≤ 75 and smoke development ≤ 450 meet code requirements for foam plastic roof insulation. Codes exempt foam plastic insulation when used in FM 4450 or UL 1256.

* Physical properties shown are based on data obtained under controlled conditions and are subject to normal manufacturing tolerances.

Thickness	Avg. LTTR	Flute Span	Qty / Pallet	SF/Pallet		Pallet/TL	
				4x4	4x8	4x4	4x8
1.0"	5.7	2-5/8"	48	768	1,536	48	24
1.1"	6.3	2-5/8"	41	656	1,312	48	24
1.3"	7.4	2-5/8"	35	560	1,120	48	24
1.5"	8.6	4-3/8"	32	512	1,024	48	24
1.8"	10.3	4-3/8"	25	400	800	48	24
2.0"	11.4	4-3/8"	24	384	768	48	24
2.2"	12.6	4-3/8"	21	336	672	48	24
2.5"	14.4	4-3/8"	19	304	608	48	24
2.6"	15.0	4-3/8"	18	288	576	48	24
*3.0"	17.4	4-3/8"	16	256	512	48	24
*3.3"	19.2	4-3/8"	14	224	448	48	24
*3.5"	20.5	4-3/8"	13	208	416	48	24
*4.0"	23.6	4-3/8"	12	192	384	48	24
*4.5"	26.8	4-3/8"	10	160	320	48	24

*LTTR (long term thermal resistance) values were determined in accordance with CAN/ULC-S770 at 75°F (24°C). Test samples were third-party selected and tested by an accredited material testing laboratory.

*To minimize the effects of thermal bridging, IB recommends the use of multiple layers when the total desired or specified R-value requires an insulation thickness greater than 2.7" thick.



Application:

IB Energy Board II can be installed over approved substrates. Refer to IB Specifications and Construction Details for additional installation instructions.

Multi-Layer Installation:

Improved insulation thermal performance and a reduction of thermal bridging can be obtained by the installation of two or more layers with all joints offset. Avoid continuous vertical joints on all multi-layer applications by staggering and offsetting the joints of each layer from those of preceding layers.

Storage & Limitations:

Insulation must be protected from open flame and always kept dry.

Store above ground on pallets and cover with breathable tarpaulins.

Install only as much insulation as can be covered the same day with the completed roofing system.

Do not leave exposed.

Go to <https://ibroof.com/tds> for the most up-to-date version of this document.

Toll Free: 800-426-1626

Care has been taken to ensure that the contents of this publication are accurate, however IB Roof Systems and any subsidiary companies do not accept responsibility for errors or for information that is found to be misleading. Suggestions for, or description of, the end use of application of products or methods of working, are for information only and IB Roof systems and any subsidiary accept no responsibility in respect thereof.