

## Product Description:

IB PVC Single Ply FB 80 is a polyester scrim reinforced, compounded PVC resin-based sheet with plasticizers, stabilizers, fillers, pigments, and other proprietary materials meeting ASTM D4434, Type III. Rolls are manufactured in a nominal 80 mil thickness and use an anti-wicking scrim for added strength, tear resistance and enhanced moisture resistance. The underside of the membrane has a tough polyester fleece backing compatible with both adhered and mechanically fastened applications.

## Packaging:

Size	Sq. Ft.	Weight per roll (approx.)
6' x 60'	360 sq. ft.	200 lbs.

## Features:

- Premium calender-film laminated, compounded, and manufactured
- Meets and exceeds ASTM D 4434-15, Type III Thermoplastic Membrane
- Excellent flexibility in all climates
- Highly reflective IB PVC can help to reduce heat transfer through the roof into the building's interior
- Thick, heavy duty 38-mil top ply weathering film
- Thermally welded seams provide superior seam strength
- Exceeds Energy Star™ and California Title 24 requirements for Solar Reflectance and Emissivity (White)
- 3.5 oz fleece backing for enhanced performance

## Use:

IB PVC Single Ply FB 80 can be installed in new, recover, and re-roof constructions as the primary field membrane and base flashing at all roof to wall transitions. It can be adhered or mechanically attached to a properly prepared substrate with approved fasteners and membrane plates or approved membrane adhesive.

## Warranties:

IB PVC Single Ply FB 80 Warranty options when installed by IB Authorized Applicators subject to IB Roof Systems specifications and warranty requirements:


- Lifetime Residential Limited Material Warranty
- 25 Year Residential Limited Material Warranty
- 25-30 Year Commercial Limited Material Warranty
- 25 Year Warranty Plus Labor & Material Warranty
- 10-30 Year Total Systems Warranty

## Available Colors:

White

## Approvals:

IB PVC membranes are listed with various component assemblies at UL and Factory Mutual (FM Global) for fire, wind uplift and impact resistance. Visit our website for links to these agencies and listings at: [www.ibroof.com](http://www.ibroof.com).



Solar Reflectance / Thermal Emittance / Calculated SRI Values					
Membrane Color	Solar Reflectance	Thermal Emittance	SRI Value Initial	SRI 3-Year Aged	LRV
White	0.87	0.88	110	91	94.3

Property	ASTM Method	Requirement	80 Mil
Overall thickness, PVC sheet, min. (in.)	D751	0.045	0.080
Thickness over scrim	D7635	0.016	0.038
Breaking strength, min. (lb/in)	D751	200 X 200	438 x 408
Elongation at the break, min. %	D751	15 <sup>A</sup> X15 <sup>A</sup>	35 x 34
Retention of properties after heat aging (min. % of original):			
Breaking strength	D751	90	Pass
Elongation	D751	90	Pass
Tear strength, min. (lb)	D751	45.0	75 x 95
Low temperature bend	D2136	-40F	Pass
Accelerated weathering test:	G154		
Cracking (7x magnification)		None	None
Crazing (7x magnification)		None	None
Linear dimension change, max %	D1204	+/- 0.5	-0.30 MD 0.10 XMD
Change in weight after immersion in water, %	D570	+/- 3.0	0.9
Static puncture resistance	D5602	Pass	Pass
Dynamic puncture resistance	5635	Pass	Pass

<sup>A</sup>For reinforcing fabric only, elongation of PVC material shall be 250% MD and 220% XMD

The table presents typical properties of IB PVC membranes. Requirements are taken from ASTM D4434-15.

Recycle Content	
Pre-Consumer	20%
APPLICATION	
ADHERED (FA)	MECHANICALLY ATTACHED (MA)