



Product Description:

IB TPO LVOC Adhesive is a one-part low VOC, synthetic polymer-based adhesive designed for bonding IB TPO SM Membranes in a two-sided 'contact-style' method.

Compatible with:

- wood
- concrete
- approved polyisocyanurate insulations
- other cover boards rated for adhered applications

Use:

- May be rolled or brushed on
- Ideal for vertical flashing applications
- Not to be used with IB TPO FB Membranes

Packaging:

5 gallon container	45/pallet
42 lbs (19.1 Kg) *7.6 lbs/gallon	1,890 lbs/pallet

Color:

Yellow

Approvals:



Refer to individual assembly approvals for additional information and requirements.

Temperature Guidelines/Storage & Handling:

Store in a dry area, indoors, out of direct sunlight in the original unopened container.

Optimum product storage temperature: 60-80°F (15-27°C) for 24 hours prior to use.

Internal Chemical Temperature at Application: Warm or cool product temperature to 60-80°F/15-27°C prior to use. If adhesive falls below 32°F (0°C), return to warm area until material temperature has reached 60°F (15°) or greater.

Outside Application Temperature: Ambient temperature is 25°F (-4°C) and rising.

Substrate Surface Temperature Range: 25-100°F (-4-38°C). Temperatures above or below Optimal Application range require additional monitoring and may affect tack/cure times, adhesion performance and application rates.



Product details stated are nominal as manufactured, and the results of tests and/or calculations and therefore are non-binding and do not represent a guarantee or warranted characteristics. User and/or designer are responsible for confirming suitable performance for specific application and conforming with all applicable laws and regulations.

Physical Properties

VOC	<250 g/L (EPA Method 24)
Specific Gravity	0.9
Shelf Life	12 months from date of manufacture
Coverage Rates*	
2-sided**	50-90 ft ² /gal

*Coverage varies depending on job site conditions, ambient and adhesive temperature and the porosity of the substrate the adhesive is applied to.

**For two-sided application, half of the adhesive is applied to the substrate and half of the adhesive is applied to the membrane.

Limitations:

- Do not use when ambient, substrate or product temperatures are outside specified temperature ranges.
- Do not use during inclement weather, on wet surfaces or on any substrate showing signs of deterioration or loss of structural integrity.
- Do not apply adhesive when dew point is within 10°F or closer to the ambient temperature.
- Do not apply adhesive if there is a possibility of temperatures falling below 25°F (-4°C) within 24 hours of application.
- Use open containers within 48 hours of opening. Replace lid on can when not in use. Adhesive that has changed color or viscosity is no longer usable.
- Do not thin.
- Do not use after the expiration date.



Application:

Refer to IB TPO Specifications and Construction Details for additional installation instructions.

- IB TPO LVOC Adhesive should be applied to a structurally sound substrate that is clean, dry, free of frost, oils, soaps, silicone, or loose material that may inhibit bonding.
- Adhesive should be applied at temperatures of 25°F (-4°C) and rising. Do not apply adhesive if there is a possibility of temperatures falling below 32°F 0°C) within 24 hours of application. Stir adhesive thoroughly before use.
- IB TPO LVOC Adhesive should be evenly applied with 3/8" medium nap solvent resistant roller or squeegee to the approved substrate.
- For two-sided applications apply at the approximate rate of one gallon per 50-90 square feet applying half of the adhesive to the substrate and half of the adhesive to the underside of the membrane.
- Roll membrane with a vinyl roller to make positive contact with substrate and to remove any air bubbles.

Note: Do not apply adhesive near seams or splices where a hot-air welder will be used.

Refer to [www.ibroof.com](http://ibroof.com) for additional installation instructions.

Go to <https://ibroof.com/tds> for the most up-to-date version of this document.

Toll Free: 800-426-1626

Care has been taken to ensure that the contents of this publication are accurate, however IB Roof Systems and any subsidiary companies do not accept responsibility for errors or for information that is found to be misleading. Suggestions for, or description of, the end use of application of products or methods of working, are for information only and IB Roof systems and any subsidiary accept no responsibility in respect thereof.