

IB PVC MEMBRANE COLOR SELECTION AND RATING GUIDE

Six **IN STOCK** colors for your demanding projects.






WHITE

50mil 60mil 80mil
● ● ●

Solar Reflectance	0.870
Thermal Emittance	0.88
SRI Value Initial	110
SRI Value 3-Year Aged	91
LRV	94.3

*Available in Fleeceback and ChemGuard



BRONZE

50mil 60mil 80mil
○ ● ●

Solar Reflectance	0.079
Thermal Emittance	0.87
SRI Value Initial	2
SRI Value 3-Year Aged	N/A
LRV	7.2



COOL STONE

50mil 60mil 80mil
○ ● ○

Solar Reflectance	0.77
Thermal Emittance	0.87
SRI Value Initial	95
SRI Value 3-Year Aged	75
LRV	N/A



GRAY

50mil 60mil 80mil
● ● ●

Solar Reflectance	0.163
Thermal Emittance	0.88
SRI Value Initial	13
SRI Value 3-Year Aged	N/A
LRV	18.1



COOL SAND

50mil 60mil 80mil
○ ● ○

Solar Reflectance	0.77
Thermal Emittance	0.87
SRI Value Initial	95
SRI Value 3-Year Aged	78
LRV	69.7



TAN

50mil 60mil 80mil
● ● ○

Solar Reflectance	0.366
Thermal Emittance	0.87
SRI Value Initial	39
SRI Value 3-Year Aged	N/A
LRV	30.2

For more information about IB membrane specifications and details please visit IBroof.com. Colors as shown are for illustration purposes. Please refer to an actual sample for full color consideration. Request a sample online at www.IBroof.com/samples-and-literature/